

ABSTRACT

The present invention provides a process for regenerating a spent aromatics alkylation or transalkylation catalyst comprising a molecular sieve by contacting the spent catalyst with an oxygen-containing gas at a temperature of about 120 to about 600°C and then contacting the catalyst with an aqueous medium, such as an ammonium nitrate solution, an ammonium carbonate solution or an acetic acid solution.

5